

Blush - "Doucement Rouge"

Ref: CC0008

Color Cosmetics

Product Name	INCI Name	%WW	Supplier
A			
Softouch CCS 102	Boron Nitride	12.70	www.advceramiccos.com
Prestige® Soft Fire-red	Mica (and) Iron Oxides	4.55	www.sudarshan.com
Silk Mica	Mica	4.55	www.vwr.com
Plastic Powder D-400	HDI/ Trimethylol Hexyl-Lactone Crosspolymer (and) Silica	5.76	www.jandekker.com
Covasilic 15	Silica Dimethyl Silylate	0.27	www.lcw.fr
Kaolin Pharma	Kaolin	2.70	www.avokal-heller.de
Dow Corning 9701 Cosmetic Powder	Dimethicone/ Vinyl Dimethicone Crosspolymer and Silica	3.60	www.dowcorning.com
B			
Zilgel Oil	Glycerin (and) Water (and) Sodium Polyacrylate (and) PVM/MA Copolymer	6.50	www.presperse.com
C			
Covacryl E 14	Acrylates Copolymer	4.10	www.lcw.fr
D			
Zilgel SM	Glycerin (and) Water (and) Sodium Polyacrylate	54.45	www.presperse.com
E			
Water Melon	Fragrance	0.36	www.mane.com
Germaben II	Propylene Glycol, Diazolidinyl, Urea, Methylparaben, Propylparaben	0.46	www.ispcorp.com

Procedure

1. Mix phase A with speed mixer (2000 rpm, 1 min)
2. Add phase B and mix with speed mixer (2400 rpm, 30 s)
3. Add phase C and mix with speed mixer (2400 rpm, 30 s)
4. Add phase D and mix with speed mixer (2400 rpm, 30 s)
5. Pass mixture through three-roll-mill for three times. While passing through add phase E

Stability

Stable for at least 6 months at RT and 40°C.

Sudarshan Chemical Industries Ltd.

Global Head Office:
162 Wellesley Road, Pune
411001, India
Tel : +91 20 260 58 888
Fax : +91 20 260 58 222
e-mail : cosmeticpigments@sudarshan.com

Sudarshan Europe BV

Crystal tower, 24th floor, Orlyplein 10,
PO Box 58176, 1040 HD, Amsterdam,
The Netherlands
Tel: +31 (0)20 475 2311
Fax: +31 (0)20 475 2312
e-mail: eu@sudarshan.com

Sudarshan North America Inc.

76 N. Walnut street,
Ridgewood NJ,
USA 07450.
Tel: +1 201 882 2135
Fax: +1 201 882 0157
e-mail: usa@sudarshan.com