

## Lipstick - "Soft Bronze"

Ref: CC0332

Color Cosmetics

Product Name	INCI Name	%WW	Supplier
<b>A</b>			
Ewacera 34	Carnauba Wax	4.50	<a href="http://www.wagnerlanolin.de">www.wagnerlanolin.de</a>
Ewacera 12	Bees Wax	3.50	<a href="http://www.wagnerlanolin.de">www.wagnerlanolin.de</a>
Ewacera 42	Candelilla Wax	4.00	<a href="http://www.wagnerlanolin.de">www.wagnerlanolin.de</a>
Parcera MW	Microcrystalline Wax	7.20	<a href="http://www.paramelt.com">www.paramelt.com</a>
Walrath Synthetic	Cetyl Palmitate	2.00	<a href="http://www.kahlwax.de">www.kahlwax.de</a>
Softisan 100	Hydrogenated Coco-Glycerides	5.00	<a href="http://www.sasolwax.com">www.sasolwax.com</a>
Penreco Blond	Petrolatum	5.80	<a href="http://www.penreco.com">www.penreco.com</a>
Luvitol EHO	Cetearyl Octanoate	10.70	<a href="http://www.basf.com">www.basf.com</a>
dl-alpha-Tocopherylacetate	Tocopheryl Acetate	0.50	<a href="http://www.dsm.com">www.dsm.com</a>
Castor Oil	Castor Oil	39.60	<a href="http://www.riedeldehaen.com">www.riedeldehaen.com</a>
<b>B</b>			
Prestige® Soft Bronze	Mica (and) Iron Oxides	17.00	<a href="http://www.sudarshan.com">www.sudarshan.com</a>
Rokonsal SSH-1	Methylparaben, Propylparaben	0.20	<a href="http://www.biochema.com">www.biochema.com</a>

### Procedure

1. Heat phase A to 85°C
2. Add phase B to phase A and mix
3. Pour into a lipstick mould at 75°C

### Stability

Stable for at least 6 months at RT and 40°C.

#### Sudarshan Chemical Industries Ltd.

Global Head Office:  
162 Wellesley Road, Pune  
411001, India  
Tel : +91 20 260 58 888  
Fax : +91 20 260 58 222  
e-mail : [cosmeticpigments@sudarshan.com](mailto:cosmeticpigments@sudarshan.com)

#### Sudarshan Europe BV

Crystal tower, 24th floor, Orlyplein 10,  
PO Box 58176, 1040 HD, Amsterdam,  
The Netherlands  
Tel: +31 (0)20 475 2311  
Fax: +31 (0)20 475 2312  
e-mail: [eu@sudarshan.com](mailto:eu@sudarshan.com)

#### Sudarshan North America Inc.

76 N. Walnut street,  
Ridgewood NJ,  
USA 07450.  
Tel: +1 201 882 2135  
Fax: +1 201 882 0157  
e-mail: [usa@sudarshan.com](mailto:usa@sudarshan.com)