

Lip Gloss - "Super Soft Silver"
Ref: CC0733

Color Cosmetics

Product Name	INCI Name	%WW	Supplier
A		100.00	
Versagel ME 1600	Hydrogenated Polyisobutene (and) Ethylene/ Propylene/ Styrene Copolymer (and) Butylene/ Ethylene/ Styrene Copolymer	72.50	www.penreco.com
Shea Oil - Ultra Refined	Butyrospermum Parkii Oil	3.00	www.biochemica.com
Silcare Silicone 31M50	Caprylyl Trimethicone	7.00	www.clariant.com
Silcare Silicone 41M65	Stearyl Dimethicone	3.00	www.clariant.com
Nexbase 2004 FG	Hydrogenated Polydecene	5.00	www.jandekker.com
Isopropyl Myristate	Isopropyl Myristate	4.50	www.vwr.com
B			
Prestige Super Soft Silver	Mica (and) Titanium Dioxide	5.00	www.sudarshan.com

Procedure

1. Heat up phase A to 85°C
2. Add phase B to phase A and mix until uniform
3. Pour into a lip gloss container

Stability

Stability data for this formulation is not yet completed.

Sudarshan Chemical Industries Ltd.

Global Head Office:
162 Wellesley Road, Pune
411001, India
Tel : +91 20 260 58 888
Fax : +91 20 260 58 222
e-mail : cosmeticpigments@sudarshan.com

Sudarshan Europe BV

Crystal tower,24th floor, Orlyplein 10,
PO Box 58176, 1040 HD, Amsterdam,
The Netherlands
Tel: +31 (0)20 475 2311
Fax: +31 (0)20 475 2312
e-mail: eu@sudarshan.com

Sudarshan North America Inc.

76 N. Walnut street,
Ridgewood NJ,
USA 07450.
Tel: +1 201 882 2135
Fax: +1 201 882 0157
e-mail: usa@sudarshan.com