Technical Data Sheet





Product Name : Sumica [™] Super Flash Gold	Color : Gold	Appearance : Lustrous Powder

Chemical Composition

Ingredient	% Composition	C. I. Number	CAS Number	EINCES Number
Mica	68-80	77019	12001-26-2	310-127-6
Titanium Dioxide	18-26	77891	13463-67-7	236-675-5
Red Iron Oxide	1-4	77491	1309-37-1	215-168-2
Tin Oxide	< 1	77861	18282-10-5	242-159-0

Physical Properties Parameter Value Unit Method Remark TiO₂ modification Rutile -ASTM D3720 _ Volatile matter Max 1 % ISO 787-2 At 105ºC, 2 h Oil absorption 70-80 g/100g ISO 787-5 pH value 6-10 _ ISO 787-9 10% Aq. Suspension Sp. Gravity 3.1 ± 0.2 _ IS 33 Part B _ Apparent density 0.6 ± 0.1 g/cc ISO 787-11 Water solubility Max 1 % IS 3493 Practically Insoluble Heat stability 800 °C Sudarshan CPTL/301 _ Resistance to dilute acid and Stable 1-5 Scale Sudarshan CPTL/301 alkali Determined on Particle size range 15-150 Sudarshan EP/1020 Malvern Particle μm (85% within range) Size Analyzer 1-8 Blue Wool 8 Light Fastness Sudarshan CPTL/301 Scale

Disclaimer : The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.

Sudarshan Chemical Industries Ltd.

HO: 7th Floor, Eleven West Panchshil, Baner, Pune - 411045, Maharashtra, India Tel: +91 20 682 81 200 | Email: contact@sudarshan.com | www.sudarshan.com Issue No : 03/Apr-23 Reviewed on: -For latest version visit www.sudarshan.com

